

**AMENDMENTS TO THE CLAIMS:**

This listing of claims will replace all prior versions, and listings, of claims in the application:

**LISTING OF CLAIMS:**


1. - 14. (Cancelled)

15. (Currently Amended) A method for using an adhesive emulsion, the method comprising:

applying the adhesive emulsion to join together at least two surfaces, wherein the adhesive emulsion comprises:

an isocyanate composition (a) with a mass content of N=C=O function of between 10% and 30% and with a viscosity of not more than 2500 mPa.s;

a surfactant (b) comprising a compound or a mixture of compounds of mean general formula:



wherein:

p represents a value between 1 and 2;

m represents zero or 1;

the sum  $p+m+q$  is equal to 3;

the sum  $1+p+2m+q$  is equal to 3 or 5;

X is an oxygen;

X' is an oxygen;

n and s have the same statistical value, chosen between 5 and 30,

wherein  $R_1$  and  $R_2$ , which are different or identical, are ~~substituted or unsubstituted aliphatic radicals with no aromatic nucleus~~ alkyl groups having 8 to 20 carbon atoms; and

an aqueous phase with a pH of between 4 and 9, optionally bearing an adhesive polymer,

wherein the isocyanate composition (a), the surfactant (b), and the aqueous phase optionally bearing an adhesive polymer are added simultaneously or successively to form the adhesive emulsion, and

wherein the adhesive emulsion includes particles having a particle size  $d_{50}$  of not more than 25  $\mu\text{m}$ , and the ~~adhesive emulsion~~ isocyanate has a polydispersity index of not more than 1.5.

16. (Previously Presented) The method for using the adhesive emulsion as claimed in claim 15, wherein the viscosity is not more than 2000 mPas.


17. (Previously Presented) The method for using the adhesive emulsion as claimed in claim 15, wherein the mass of the agent b) (numerator) and the mass of the composition a) (denominator) has a ratio ranging from 2% to 10.


18. (Previously Presented) The method for using the adhesive emulsion as claimed in claim 15, wherein the sum  $p+q$  is equal to 2.

19. (Previously Presented) The method for using the adhesive emulsion as claimed in claim 15, wherein said isocyanate composition a) comprises at least 50% by mass of oligomers chosen from hetero- and homooligomers, at least one of the monomers of which is an aliphatic monomer bearing at least two isocyanate functions and whose skeleton, on the shortest trajectory connecting two isocyanate functions, comprises at least one polymethylene sequence of at least two methylene chain units  $(CH_2)_\mu (\mu \geq 2)$ , which is exocyclic when the monomer comprises a ring.

20. (Previously Presented) The method for using the adhesive emulsion as claimed in claim 15, wherein said isocyanate composition a) further comprises a portion of reactive solvent comprising at least one molecule chosen from dimers, bis-dimers, monoallophanates, polymethylene diisocyanates and di-, tri- or tetrafunctional monomers with a molecular mass at least equal to 200.

21. (Previously Presented) The method for using the adhesive emulsion as claimed in claim 20, wherein said portion represents a portion ranging from 5% to 20% by mass of the isocyanate composition a).





wherein:

p represents a value between 1 and 2;

m represents zero or 1;

the sum  $p+m+q$  is equal to 3;

the sum  $1+p+2m+q$  is equal to 3 or 5;

X is an oxygen;

X' is an oxygen;

n and s have the same statistical value of between 5 and 30,

wherein  $R_1$  and  $R_2$ , which are different or identical, are ~~substituted or unsubstituted aliphatic radicals with no aromatic nucleus~~ alkyl groups having 8 to 20 carbon atoms;

and

an aqueous phase with a pH of between 4 and 9, optionally bearing an adhesive polymer,

wherein the isocyanate composition (a), the surfactant (b), and the aqueous phase optionally bearing an adhesive polymer are added simultaneously or successively to form the adhesive emulsion, and

wherein the adhesive emulsion includes particles having a particle size  $d_{50}$  of not more than 25  $\mu\text{m}$  and, and the ~~adhesive emulsion~~ isocyanate has a polydispersity index of not more than 1.5.

31. (Previously Presented) The method for using the adhesive emulsion as claimed in claim 15, wherein the isocyanate composition (a) with a mass content of N=C=O function of from 15% to 25% and with a viscosity of not more than 1500 mPa.s.

32. (Previously Presented) The method for using the adhesive emulsion as claimed in claim 15, wherein the sum  $1+p+2m+q$  is 5.

33. (Previously Presented) The method for using the adhesive emulsion as claimed in claim 15, wherein n and s have the same statistical value, chosen between 9 and 20.

34. Canceled

35. (Currently Amended) The method for using the adhesive emulsion as claimed in claim 15, wherein the adhesive emulsion includes particles having a particle size  $d_{50}$  of not more than 22  $\mu\text{m}$ , and the ~~adhesive emulsion~~ isocyanate has a polydispersity index of not more than 1.3.

36. (Previously Presented) The method for using the adhesive emulsion as claimed in claim 15, wherein the mass of the agent b) (numerator) and the mass of the composition a) (denominator) has a ratio ranging from 3% to 7%.

37. (Previously Presented) The method for using the adhesive emulsion as claimed in claim 15, wherein said isocyanate composition a) comprises at least 70% by mass of oligomers chosen from hetero- and homooligomers, at least one of the monomers of which is an aliphatic monomer bearing at least two isocyanate functions and whose skeleton, on the shortest trajectory connecting two isocyanate functions, comprises at least one polymethylene sequence of at least two methylene chain units  $(CH_2)_\mu (\mu \geq 2)$ , which is exocyclic when the monomer comprises a ring.

38. (Previously Presented) The method for using the adhesive emulsion as claimed in claim 15, wherein the viscosity is not more than 1200 mPa.s.

39. (Previously Presented) The method for using the adhesive emulsion as claimed in claim 30, wherein the isocyanate composition (a) with a mass content of N=C=O function of from 15% to 25% and with a viscosity of not more than 1500 mPa.s.

40. (Previously Presented) The method for using the adhesive emulsion as claimed in claim 30, wherein the sum  $1+p+2m+q$  is 5.

41. (Previously Presented) The method for using the adhesive emulsion as claimed in claim 30, wherein n and s have the same statistical value, chosen between 9 and 20.

42. Canceled

43. (Currently Amended) The method for using the adhesive emulsion as claimed in claim 30, wherein the adhesive emulsion includes particles having a particle size  $d_{50}$  of not more than 22  $\mu\text{m}$ , and the ~~adhesive emulsion~~ isocyanate has a polydispersity index of not more than 1.3.